

Resene product labels are updated from time to time. This label is provided as a guide for this product and may differ from the label on the container you purchase.  
Please discuss your project with your local Resene ColorShop team or reseller to ensure you have the right products to give you the best quality finish for your specific project.

**WARNING**

Read label before use. Keep out of reach of children. Causes skin irritation. May cause an allergic skin reaction. Causes eye irritation. May damage fertility or the unborn child. May cause respiratory irritation. May cause dizziness or drowsiness. Very toxic to aquatic life with long lasting effects.

**PRECAUTIONS**

DO NOT BREATHE FUMES/MISTS/SPRAYS/VAPOURS. DO NOT EAT, DRINK, OR SMOKE WHILE USING.

Do not handle until all safety precautions have been read and understood. Store in original or correctly labelled container, tightly closed, in a well ventilated area indoors, away from foodstuffs, either between 15°C-20°C or at a cool, constant temperature. Store locked up. Ground/bond container and receiving equipment. Use explosion-proof electrical/ventilating/lighting equipment. Use only non-sparking tools. Take precautionary measures against static discharge. Wear protective gloves and eye/face protection. Wash thoroughly after handling. Do not allow contaminated clothing out of the workplace. Clean up spillage. Avoid release to the environment. Dispose of empty container safely. Consult Resene checklist on environmentally acceptable methods for cleaning equipment and disposing of unwanted paint.

**FIRST AID**

IF SWALLOWED: Rinse mouth.

IF ON SKIN (or hair): Remove/take off immediately all contaminated clothing. Rinse skin with water/shower. If skin irritation occurs: Get medical advice/attention.

IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do so. Continue rinsing. If eye irritation persists: Get medical attention/advice.

IF INHALED: Remove to fresh air and keep at rest in a position comfortable for breathing.

If exposed or concerned: Get medical advice/attention. When seeking medical advice take this container with you.

Further information can be obtained from  
AUST: POISONS INFORMATION CENTRE 131 126  
or call Resene 1800 738 383.

NZ: NATIONAL POISONS CENTRE 0800 POISON (764 766)  
or call Resene 0800 737 363.

CONTAINS: Dimethyl benzene 240-270 gms/L  
For use as a decorative/protective coating.

For full technical instructions see Data Sheet RA23.

**SPILLS:** Wear appropriate protective clothing. Absorb with sand or earth. Collect and seal in properly labelled drums. Do not allow to enter drains or to run off into waterways. Refer to local waste management authority.

**CLEANING PAINT EQUIPMENT:** Brush/roll out as much paint as possible on to newspaper before washing out brushes/rollers with the recommended thinner. Do not allow thinner to enter any drains. Refer to your local Council for disposal of dirty thinner.

**FIRE:** Use foam, carbon dioxide or dry chemical powder.

**WARNING**

KEEP OUT OF REACH OF CHILDREN

# Resene

## ArmourZinc 110

### cold galv zinc rich primer

**Engineered Coating Systems****GREY**

Resene ArmourZinc 110 is a high zinc content primer exhibiting the excellent corrosion resistance of zinc rich primers. Prevents underfilm corrosion at areas of damage.

**General**

- Safety Data Sheet (SDS) is available and must be consulted before use.
- In every case it is recommended that the current Resene Data Sheet is consulted for product data and surface preparation information.
- Thinning requirements may vary according to application method, equipment and environmental conditions.
- If thinning is required add recommended thinner after components have been blended and thoroughly re-mix using the power mixer.
- Ensure correct wet film thickness is applied to achieve desired dry film thickness. Allowance must be made for any thinner added.
- Use of incorrect thinner may have an adverse effect on application and performance.
- Drying is affected by low temperatures and high humidity.
- The temperature of the substrate should be 3°C above the "Dew Point".
- The "Dew Point" requirement can be presumed to be satisfied if a thin clearly defined film of water applied to the cleaned surface with a damp cloth evaporates within 15 minutes.
- Following appropriate preparation, all surfaces must be dry and clean prior to painting.
- This product may be used to paint a wide variety of surfaces. If the surface you propose to paint is unsound or not referred to, contact your local Resene ColorShop or Reseller for your nearest Technical Representative.

**Be PaintWise**

For tips on minimising the impact of your decorating on the environment see the Resene website.



UN NO. 1263 – PAINT RELATED MATERIAL

**FLAMMABLE LIQUID AND VAPOUR**

Keep away from heat/sparks/open flames/hot surfaces. No smoking.

ArmourZinc 110  
SDSArmourZinc 110  
TDS**Resene**

the paint the professionals use

In Australia: Resene Paints (Aust) Limited  
7 Production Ave, PO Box 924, Beenleigh, Qld 4207  
Phone 1800 738 383 Fax 1800 064 960

Email advice@resene.com.au or visit www.resene.com.au

In New Zealand: Resene Paints Limited  
Vogel Street, PO Box 38242, Wellington Mail Centre, Lower Hutt 5045  
Phone (04) 577 0500 Fax (04) 577 0600

Email advice@resene.co.nz or visit www.resene.co.nz

Manufactured under a quality system certified as complying with ISO9001 by Telarc SAI, an accredited certification body. Printed on environmentally responsible paper, which complies with the requirements of environmental management systems EMAS and ISO14001, using vegetable-based inks.

**Quick check**

**Name:** Resene ArmourZinc 110.

**Generic type:** Single pack organic zinc rich primer.

**Colours:** Grey.

**Finish:** Matt.

**Application method:** Conventional spray. Small areas only may be brushed.

**Recommended dry film thickness (D.F.T.):** 75 microns per coat.

**Theoretical coverage:** 6.3 square metres per litre at 75 microns D.F.T.

**Dry time (minimum):** Touch dry: 20 minutes at 18°C. Hard dry: 4 hours at 18°C. Drying is affected by low temperatures and high humidity.

**Recoat time (minimum):** Minimum: 4 hours at 18°C. May be overcoated with acrylics, alkyds, chlorinated rubber systems, vinyls (see limitations).

**Usual number of coats:** 1 (spray application) at 6.3 sq. metres per litre. 2 (brush application) at 12.6 sq. metres per litre.

**Thinning and clean up:** Resene Thinner No.6 (spray application). Resene Thinner No.11 (brush application).

**Resene Data Sheet:** RA23.

**Limitations:** Not suitable for overcoating with two component (2K) priming or finishing systems. A non-saponifiable barrier coat such as Resene Galvo-One (Data Sheet D41) MUST BE USED when overcoating with alkyd or oil-based systems. Apply Resene Galvo-One or Resene Galvo-Prime (Data Sheet D402) BEFORE APPLICATION of acrylic topcoats.

**Enjoy the Resene Promise of quality on premium paints.** See your Resene ColorShop or the Resene website for a copy.

**In every case it is recommended that the appropriate Data Sheet and Safety Data Sheet are consulted prior to application.**

Please ensure that use of this product is compatible with the substrate and surface preparation method and that the colour in this container is the same as selected. When using multiple packs of this product on the same project please mix them together before use. Resene does not accept any responsibility for the application of incorrect product to substrate or the application of incorrect colours. For further painting advice and information, call 1800 738 383 (AUST), 0800 737 363 (NZ) or visit the Resene website.